

Recycled, coloured board with a soft surface, especially developed for letterpress applications

Basis weight	ISO 536	g/m <sup>2</sup>	330	530
Thickness / Caliper	ISO 534	µm	520	840
Specific Volume / Bulk	ISO 534	cm <sup>3</sup> /g	1,6	1,6
Cobb 60 sec.	ISO 535	g/m <sup>2</sup>	50	50
pH value	ISO 6588	pH	7	7

All properties are according to mill measurements that may be subject to fluctuations which are customary within the industry

## Applications

- Cards, Desktop displays, Floor displays, Signs, Tags, Covers for books and brochures, Calendar backs, Handicrafts

## Environmental product certificates and information

- Produced from 100% recycled fibres

## Supplier certificates

- Quality Management System (ISO 9001)

**Technical capability**

Printing technologies:	Non-absorbent substrate that is suitable for offset, UV-offset and screen printing. A sufficient quantity of printing powder with the appropriate particle size has to be considered. Colour variations and differences in the surfaces from sheet to sheet, as well as frequent inclusions and impurities, are characteristic for this product. Complaints based on these grounds cannot be accepted.
Screen ruling:	All conventional screen rulings up to 60 l/cm (150 lpi) are applicable. When using other screen technologies, tests are recommended before print production.
Printing inks:	Suitable are purely oxidative drying inks (Offset), UV-inks and screen printing inks. Take care of an optimum ink-water balance.
Ink drying:	The drying process of oxidative drying offset ink is entirely completed within 24 to 48 hours, depending on the thickness of the ink film.
Printing pressure:	Standard pressure. Slightly increased pressure on bulky papers and usage of soft rubber blankets is recommended.
Finishing:	Varnishing with overprint and water-based varnishes, as well as hot foil stamping, embossing and die-cutting are applicable. A finishing with UV-varnish has to be checked in advance and could require a pre-coating with a primer.
Hot foil stamping:	suitable
Creasing & folding:	In order to obtain the best possible folding results, the folding process has to be prepared via creasing, while the common standard values for creasing have to be considered.
Handling information:	The flatness of this paper is guaranteed at a relative humidity between 45 and 55% at a temperature between 20 and 23°C. It is recommended that the printing room has comparable climatic conditions. The paper should be kept as long as possible in the mill-wrapper before use. Extreme changes in temperature and humidity should be avoided.

For all printing and processing techniques, the recommendations of the manufacturers of machines, inks, adhesives, laminating and embossing foils, etc. are to be followed. For damages caused by faulty implementation of printing and processing, Papyrus cannot accept any liability.

Can be subject to printing errors and modifications