

Technical specification

Certified according to ISO EN 9001 / EN ISO 14001

Grade	ALGRO DESIGN	6240	Customer
--------------	--------------	------	-----------------

Productdescription	Solid bleached board (SBB) woodfree, white, silk, one side double coated, high UV-light fastness and high resistance to ageing. Suited for direct food contact in accordance with recommendation BfR XXXVI, FDA and Austrian food legislation, taint and odour neutral. Optionally available as PEFC and FSC.
Conversion	Lacquering - UV, water based and conventional, foil and film lamination, hot foil stamping and cold foil transfer, embossing (high, relief, structure, micro), die cutting, creasing, grooving, perforating, flock coating, lasercodable.
Application	High quality packaging and graphic applications.
Printing	Offset, screen and flexographic printing

Test climate 23° C, 50 % relative humidity, DIN EN 20 187 All rights to improve quality due to technical modifications reserved

Form number: ABA-PFS-AWT-001-01/C 09/02	Revision: G 05/10 ersetzt F 03/10
--	--

Property	Unit	Standard	Target value										Tolerance
			160.0	220.0	240.0	270.0	300.0	330.0	350.0	380.0	400.0		
Grammage	g/m ²	DIN ISO 536	160.0	220.0	240.0	270.0	300.0	330.0	350.0	380.0	400.0	± 5.0%	
Thickness	µm	DIN EN 20534	181.0	255.0	281.0	323.0	365.0	405.0	435.0	470.0	495.0	± 5.0%	
Bending force (15°/50 mm) MD	mN	ISO 5628 2493	35.0	110.0	160.0	220.0	300.0	400.0	460.0	520.0	600.0	± 15.0%	
Bending force (15°/50 mm) CD	mN	ISO 5628 2493	15.0	55.0	80.0	115.0	160.0	205.0	230.0	250.0	280.0	± 15.0%	
Bending moment (15°) MD	mNm	Taber T489-om-92	1.7	5.3	7.7	10.5	14.5	19.3	22.2	25.6	29.0	± 15.0%	
Bending moment (15°) CD	mNm	Taber T489-om-92	0.7	2.6	3.9	5.6	7.7	9.9	11.4	13.0	15.5	± 15.0%	
Bending stiffness (5°/50 mm) MD	mNm	DIN 53121	3.0	9.7	13.0	18.0	27.0	37.0	43.0	52.0	61.0	Reference value	
Bending stiffness (5°/50 mm) CD	mNm	DIN 53121	1.5	4.7	6.5	9.2	14.0	19.0	23.0	26.0	30.0	Reference value	
Brightness (R457) topside	%	ISO 2470	101.5									± 1.5	
Brightness (CIE) top side	%	ISO 11475	132.0									Reference value	
L-value top side	%	ISO 5631	95.50									± 1.00	
a-Value top side	-	ISO 5631	1.80									± 0.30	
b-Value top side	-	ISO 5631	-9.00									± 1.00	
Brightness (R457) reverse side	%	ISO 2470	98.0									± 1.5	
b-value reverse side	-	ISO 5631	-8.00									± 1.00	
Surface roughness top side	µm	ISO 8791/4	2.0									± 0.6	
Moisture content abs.	%	DIN EN 20 287	5.5									± 1.0	